

# LANKO

## DESCRIPTION

Lanko 760 is a high performance reinforcement primer for the corrosion protection of steel reinforcement bars.

## USES

- To provide an alkaline passivating cover to old and new reinforcement.
- For subsequent application /bonding of concrete, cementitious or epoxy repair mortar.

## CHARACTERISTICS

- Protection against corrosion
- Excellent resistant to sea water

## SPECIFICATIONS

Form: Reddish brown liquid

Density:  $1.00 \pm 0.02$

Drying Time: Approx. 1 hour

Rust Inhibition (V) : - 0.129

## APPLICATION

### Surface Preparation

Once the designated repair area has been identified, the reinforcing bars should be exposed by hacking back (15 - 20mm behind bars) to a sound substrate. The bars should be cleaned by either blasting (to Swedish standard SA 2½) or using hand held grinding tools (to SA 2 or 3) and dusted off. The reinforcement should be free from moist, dust, oil and other contaminants before priming.

### APPLYING 760 PASSIVANT ACIER

Lanko 760 is applied direct from the can using a brush and apply evenly, do not over-apply or apply too thick.

Care must be exercised to ensure complete coverage of the exposed reinforcing bar. Subsequent repair mortars or concrete may be applied after the application of Lanko 760.

Allow Lanko 760 to dry before subsequent application of mortars or concrete.

Specifications are subject to change without notification. Results shown are typical but reflect test procedures used. Actual field performance will depend on installation methods and site conditions.

# SINGLE COMPONENT PAINT PROTECTION AGAINST CORROSION

# 760

# LANKO

## PACKAGING

Lanko 760 is packed in 5 litres can.

## STORAGE

12 months from date of manufacture if stored in unopened original packing in dry, frost-free conditions.

## PRECAUTIONS

In case of eyes splashed or excessive skin contact, thoroughly flush with water. If any ill effects should occur, seek medical attention promptly.

"The information provided in this document results from our knowledge of the products and our experience. On-site results may vary, in particular according to the product application methods adopted. Where application methods not covered by this document are used, customers must request specific additional information and/or carry out a representative test before using the products. The above-mentioned information in no way constitutes a warranty relative to the use of the products. Our general terms and conditions of sale shall prevail, in any event, on the information provided in this document. Prior to application, customers and users are requested to check that they have the latest version of this document."

## **PAREXDAVCO**

PAREXDAVCO (SINGAPORE) PTE LTD

28 Tuas South Avenue 8 Singapore 637648

Telephone: 65 6861 0532 Facsimile: 65 6862 3915

Overseas Offices: Australia (Sydney - Head Office), China, Thailand, Malaysia

Email: sales@parexdavco.com.sg Website: www.parexdavco.com.sg

